

PubliPress

Schwarz Produktion
MAXAU

PubliPress is a SC-A super calendered mechanical paper.

- High print evenness
- Suitable for rotogravure and heatset
- High print gloss

PRODUCER

Maxauer Papierfabrik GmbH

TYPICAL END USES

Mass circulation magazines
Supplements
Catalogues
Brochures
Inserts
Flyers

CHARACTERIZATION DATA

Fogra 40

ICC-PROFILE

SC_paper_eci.icc

PRINTING METHODS

HSWO
Rotogravure

L* a* b* target values	L*	a*	b*	Flourescence (ISO 12647-2)
ISO 5631-3 (D50/C2°)	88	-1,1	5,2	Faint

TECHNICAL SPECIFICATIONS (target values)

Substance		g/m ²	45	49	52	56
Brightness	ISO 2470-2 (D65/10°)	%	66	66	66	66
CIE Whiteness	ISO 11476 (C/2°)	%	43	45	45	45
Opacity	ISO 2471	%	90	91	92	94
Gloss Hunter	ISO 8254-1	%	45	45	47	47
Thickness	ISO 534	µm	41	43	44	47
Bulk	ISO 534	cm ³ /g	0,8-0,9	0,8-0,9	0,8-0,9	0,8-0,9
Smoothness	ISO 8791-4 PPS (1MPa)	µm	1,0-1,2	1,0-1,2	1,0-1,2	1,0-1,2

REEL SPECIFICATIONS MAXAU

Cores: 76 mm & 150 mm
Trimmed width: 7200 mm
Width: min. 400 mm, max. 4320 mm
Diameters: 1250 mm
Weight: max. 6800 kg

CERTIFICATES

EU Ecolabel DE/011/122
Quality ISO 9001
Environment ISO 14001
EMAS
Health & Safety ISO 45001
Energy ISO 50001
FSC®CoC
PEFC™ CoC
ISO 38200 CoC

ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.